



# LACAR<sup>®</sup> AMBIANCE

## Die Gimmel-Leder Produktion

Alle Anforderungen an die internationale Gesetzgebung, insbesondere diejenigen der EU, werden erfüllt.

Rohware: ausschliesslich europäische Rindhäute.

Gerbung: je nach Lederart mineralische Gerbung mit Chromsulfat, vegetabilische oder synthetische.

Färbung: mit Azo-Farbstoffen ohne verbotene Arylamine und Fette ohne AOX-haltige Produkte.

Zurichtung: wasserverdünnbare Lacke verschiedener Polymerverbindungen.

## Gimmel-Leather Production

International, especially European legislation is fully adopted in the leather production.

Rawhides: superior European cattle-hides are processed.

Tannage: dependent upon leather quality, mineral tannage with chromium sulphate, vegetable or synthetic tannage may be employed.

Colouring: effected with azo-dyes and fatliquors that comply with existing legislation.

Finishing: finishing effects are accomplished with water-soluble polymer-lacquers.

**Echtes Leder ist ein Naturprodukt:** der Anatomie des Tieres entsprechend bestehen innerhalb der Haut Unterschiede in der Dichte der Faserstruktur.

**Genuine leather is a product of nature:** According to the anatomy of the animal the fibre structure differs in density within a hide.

| Farben /<br>Colours | Sonderfarben /<br>Special Colours | Grösse /<br>Surface    | Stärke /<br>Thickness | Ledertyp /<br>Leather Type |
|---------------------|-----------------------------------|------------------------|-----------------------|----------------------------|
| 21                  | min. 20 Häute / Hides             | ca. 5.2 m <sup>2</sup> | 1.3-1.5 mm            | Pigmentiert / Pigmented    |

LACAR<sup>®</sup> AMBIANCE ist ein Klassiker für die internationale Polstermöbelbranche. Mit 1.4 mm Lederstärke hat das Leder mehr Substanz und Stand und bleibt formbeständig. Die gleichmässige Struktur wird durch eine Prägung verstärkt und verleiht dem Leder den edlen runden Walknarben. Finish und Griff sind sehr angenehm natürlich und doch absolut pflegeleicht.

LACAR<sup>®</sup> AMBIANCE is an accepted state of the art leather for the international furniture market. Added body and an excellent ability to maintain shape stem directly from its 1.4 mm gauge, boosting fibre substance and stand. The uniform structure of LACAR<sup>®</sup> AMBIANCE is enhanced through embossing, giving the natural look of a milled grain. Silky smooth "finish" and "hand" provide maximum appeal yet easy care.

## Technische Daten / Technical Data

| Kriterium /<br>Criteria                   | Testmethode /<br>Test Method | Anforderung /<br>Requirement |
|---|------------------------------|------------------------------|
| Lichtehtheit / Colours Fastness to Light  | ISO 105-B02                  | min. 4                       |
| Knickfestigkeit / Flexing Endurance       | ISO 5402                     | 50'000                       |
| Haftfestigkeit / Finish Adhesion          | ISO 11644                    | 2.5 N / 10 mm                |
| Reibehttheit / Colour Fastness to Rubbing |                              |                              |
| • trocken / dry                           | ISO 11640                    | 500 Cyc. / 4                 |
| • nass / wet                              | ISO 11640                    | 100 Cyc. / 4                 |
| Reissfestigkeit / Tear Resistance         | ISO 3377-1                   | 40 N                         |
| Flammfestigkeit / Flammability            | BS 5852                      | Part 2                       |